



TECHNICAL PAINT SERVICES

A23 ANTI-STATIC FINISH

Features:

A fast drying paint designed specifically to dissipate static charge, and prevent static accumulation by increasing surface conductivity. De-staticised surfaces resist dust, dirt and lint attraction. Ideal for use on floors, walls and ceilings in computer complexes, warehouses, electronic and food processing plants.

Availability:

BS4800 colour range, plus Transparent in 5 Litre containers, minimum 25 Litres, to order only.

Volume Solids:

50% ± 3% (BS 3900 Part A10).

Preparation:

The surface should be thoroughly clean, dry and free from dust and grease. Any damaged areas should be repaired and existing painted surfaces should be rubbed down with abrasive paper and cleaned with Sugar Soap before priming as follows:

ES26/70/4 Emulsion Sealer or EP26/5/4 Emulsion Primer White.

New unpainted metal or wood: AP23 Anti-Static Undercoat.

Plastic: PP129 Adhesion Promoter.

Application:

Conventional or airless spray. Apply two coats "wet on wet" when temperature is above 12°C. Do not use on heated surfaces reaching more than 60°C. Thin up to 25% by volume with UTR112 Universal Synthetic Thinners to achieve spraying viscosity of 30 - 40 seconds BSB4 cup @ 20°C.

Coverage:

Approximately 40 - 50 sq metres per 5 Litres at 25 microns dry film thickness.

Drying:

Touch dry: 10 - 15 minutes @ 20°C.

Hard dry & Recoatable: 2 - 3 hours @ 20°C.

Special Note:

Adequate through ventilation or forced extraction must be maintained during application and throughout the drying process. Barrier creams should be used for skin protection and eye protection is essential.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.
See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.

FOR PROFESSIONAL USE ONLY. READ DATA BEFORE USE.

27 SOUTHCOTE ROAD BOURNEMOUTH BH1 3SH Tel 0845 230 1244 Fax 0845 230 1255

Email enquiries@technicalpaintservices.co.uk www.technicalpaintservices.com

Technical Paint Services is the trading name of Neatcross Ltd. Registered Office as above. Company No: 1570359.