



# TECHNICAL PAINT SERVICES

## A46 SILICONE ALKYD FINISH

**Features:**

A high performance gloss paint, based on silicone alkyd resin. To be used as part of the Technical Paint Services Silicone Alkyd System over the approved primers and undercoats. A high build grade is also available.

**Availability:**

BS4800 colour range and Clear in 5, 2.5, and 1 Litre containers.

**Volume Solids:**

55% ± 3% (BS 3900 Part A10) - may vary with colour.

**Preparation:**

The substrate must be thoroughly clean, dry and free from corrosion, dust and grease. Use over AP46 Silicone Alkyd Undercoat and suitable primer. Previously glossed surfaces should be flatted or washed with sugar soap solution and rinsed.

**Application:**

Brush, roller or conventional spray. Avoid damp conditions. Do not apply if dew point is reached. Do not apply at less than 10°C. When spraying, thin using UTR112 Universal Synthetic Thinners. For brushing and cleaning use X156 White Spirit.

**Coverage:**

Approximately 45 sq metres per 5 Litres, giving 25 microns dry film thickness.

**Drying:**

Touch dry: 30 minutes @ 20°C.

Hard dry: 12 hours @ 20°C.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.

See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.