



TECHNICAL PAINT SERVICES

AP72/5 PHOSPHORESCENT UNDERCOAT

Features:

A high quality, fast drying undercoat to use in conjunction with A72/30 Phosphorescent Finish. Suitable for direct application to ferrous metals and wood. For priming all other surfaces see below.

Availability:

White in 5, 2.5 and 1 Litre containers.

Volume Solids:

55% ± 3% (BS 3900 Part A10).

Preparation:

The substrate must be thoroughly clean, dry and free from corrosion, dust and grease. The following primers are recommended:

- Galvanised Steel: Apply X85 Mordant Solution followed by AP72/5 Phosphorescent Undercoat White.
Aluminium & Alloys: Apply UP89/25 Two Pack Etching Primer followed by AP72/5 Phosphorescent Undercoat White.
Asbestos & Concrete: Apply RL10/70/1 Chlorinated Rubber Clear, followed by AP72/5 Phosphorescent Undercoat White.
Plastic: Apply PP129 Adhesion Promoter followed by AP72/5 Phosphorescent Undercoat White.

Application:

By brush, roller or conventional spray. Thin up to 25% by volume with UTR112 Universal Synthetic Thinners to achieve a spraying viscosity of 25 - 30 seconds BSB4 cup @ 20°C.

Coverage:

Approximately 40 - 50 sq metres per 5 Litres @ 25 microns dry film thickness.

Drying:

- Touch dry: 15 - 20 minutes @ 20°C.
Hard dry: 30 minutes - 1 hour @ 20°C.
Recoatable: 1 hour @ 20°C.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.
See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.