



# TECHNICAL PAINT SERVICES

## AP83/65 ZINC RICH GALVANIC PRIMER

### **Features:**

A quick drying anti-corrosive primer/finish for application to ferrous metals, also suitable as a “touch in” for galvanised and zinc sprayed steel. Ideal for use on boat hulls and structural steelwork where long-term protection is required. Not suitable for “potable” liquid containers.

### **Availability:**

In 5, 2.5 and 1 Litre containers in Grey.

### **Volume Solids:**

92% ± 3% (BS 3900 Part A10).

### **Preparation:**

The substrate must be thoroughly clean, dry and free from corrosion, dust and grease. Stir the primer thoroughly before use.

### **Application:**

Supplied ready for use for brushing. Use UTR112 Universal Synthetic Thinners for cleaning and for thinning if required. Stir thoroughly before use to ensure uniform dispersion of the heavy zinc pigment. For optimum protection it is recommended that two coats be applied, allowing 24 hours drying between coats. For spraying use 50 p.s.i. or pressure fed equipment. Thin approximately 10 - 15% by volume.

### **Coverage:**

Approximately 50 sq metres per 5 Litres @ 40 microns dry film thickness.

### **Drying:**

Touch dry:	15 minutes @ 20°C.
Hard dry:	2 hours @ 20°C.
Recoatable:	24 hours.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.  
See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.