



TECHNICAL PAINT SERVICES

HP46/20/4 LOW TEMPERATURE HEAT RESISTING RED OXIDE PRIMER

Features:

A quick drying red oxide anti-corrosive primer, resistant to temperatures up to 110°C. Suitable for use under most finishes.

Availability:

5, 2.5 and 1 Litre containers.

Volume Solids:

55% ± 3% (BS 3900 Part A10).

Preparation:

The substrate must be thoroughly clean, dry and free from corrosion, dust and grease. Aluminium and galvanised surfaces should be treated with UP89 Two Pack Etching Primer prior to application of H46/20.

Application:

Conventional spray. Small areas may be brushed. Thin up to 25% by volume using UTR112 Universal Synthetic Thinners to achieve a spraying viscosity of 25 - 30 seconds BSB4 cup @ 20°C.

Coverage:

Approximately 40 - 50 sq metres per 5 Litres @ 25 microns dry film thickness.

Drying:

Touch dry: 15 minutes @ 20°C.

Hard dry & recoatable: 1 hour @ 20°C.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.
See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.