



TECHNICAL PAINT SERVICES

MP53 MARINE UNDERCOAT

Features:

A high quality marine undercoat suitable for all interior and exterior superstructures for use above the water line. It is suitable for application over any existing paintwork, with the exception of bituminous and chlorinated rubber coatings. To be used in conjunction with M53 Marine Gloss finish.

Availability:

Colour range to complement M53 finish available in 5, 2.5, and 1 Litre containers.

Volume Solids:

55% ± 3% (BS 3900 Part A10). May vary with colour.

Preparation:

The substrate must be thoroughly clean, dry and free from corrosion, dust and grease and primed with the appropriate primer. Existing painted surfaces should be thoroughly rubbed down with abrasive paper.

Application:

Brush or conventional spray. Supplied ready for use for brushing. Thin up to 25% by volume with UTR112 Universal Synthetic Thinners to achieve a spraying viscosity of 25 - 30 seconds BSB4 cup @ 20°C. Use X156 White Spirit for cleaning.

Coverage:

Approximately 40 sq metres per 5 Litres, giving a dry film thickness of 25 microns.

Drying:

6 - 8 hours, depending on temperature and humidity. Drying time can be reduced by the addition of X21 Liquid Driers.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.
See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.