



TECHNICAL PAINT SERVICES

R12 CHLORINATED RUBBER PAINT MICACEOUS IRON OXIDE

Features:

An air drying, single pack Chlorinated Rubber paint containing Micaceous Iron Oxide pigment, which affords excellent resistance to a wide range of chemicals including acids, alkalis, moist gases and mineral oil. Ideal for use in severely adverse environmental conditions when used in conjunction with other T.P.S. high performance products.

Availability:

Manufactured to order in 5 Litre containers.

Volume Solids:

62% ± 3% (BS 3900 Part A10).

Preparation:

The surface should be clean, dry and free from corrosion, dust and grease.

Application:

Brush, roller, conventional or airless spray. Supplied ready for use for brushing. Thin up to 20% by volume with UTR112 Universal Synthetic Thinners to achieve satisfactory spraying viscosity. When brushing, at least two coats will be required to achieve minimum film thickness requirements. Do not apply when substrate temperature is less than 3°C below the dew point.

Coverage:

30 sq metres per 5 Litres giving a dry film thickness of 60 microns.

Drying:

Touch dry:	30 minutes @ 20°C. 3 hours @ 5 - 10°C.
Recoatable:	8 hours @ 20°C. 12 hours @ 5 - 10°C.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.
See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.

FOR PROFESSIONAL USE ONLY. READ DATA BEFORE USE.

27 SOUTHCOTE ROAD BOURNEMOUTH BH1 3SH Tel 0845 230 1244 Fax 0845 230 1255
Email enquiries@technicalpaintservices.co.uk www.technicalpaintservices.com

Technical Paint Services is the trading name of Neatcross Ltd. Registered Office as above. Company No: 1570359.