



# TECHNICAL PAINT SERVICES

## R34 CHLORINATED RUBBER FLOOR FINISH

### **Features:**

A fast drying, single pack floor finish which has excellent resistance to a wide range of chemicals, including acids, alkalis, inorganic salts, mineral oil and water. Ideally suited for application to “green” concrete floors as R34 can be applied when concrete is 3 - 4 weeks old. This paint should not be applied over PVA sealer, latex self leveling compound or power floated concrete. Please contact our Technical Department.

### **Availability:**

BS4800 colour range made to order in minimum of 5 Litre containers. R35 Chlorinated Rubber Floor Finish Non-Slip is also available.

### **Volume Solids:**

51% ± 3% (BS 3900 Part A10).

### **Preparation:**

The surface should be clean, dry and free from dust and grease.

### **Application:**

Brush, roller, conventional or airless spray. Supplied ready for use for brushing. Thin up to 25% by volume with UTR112 Universal Synthetic Thinners to achieve a suitable spraying viscosity. R34 may be applied over RL10/70/1 Chlorinated Rubber Clear Sealer or EL56/70 Emulsion Sealer Clear.

### **Coverage:**

40 - 50 sq metres per 5 Litres @ 25 microns dry film thickness.

### **Drying:**

Touch dry:	1 hour @ 20°C. 3 hours @ 10°C.
Recoatable:	8 hours @ 20°C. 12 hours @ 10°C.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.  
See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.

**FOR PROFESSIONAL USE ONLY. READ DATA BEFORE USE.**

27 SOUTHCOOTE ROAD BOURNEMOUTH BH1 3SH Tel 0845 230 1244 Fax 0845 230 1255  
Email enquiries@technicalpaintservices.co.uk www.technicalpaintservices.com

Technical Paint Services is the trading name of Neatcross Ltd. Registered Office as above. Company No: 1570359.