



TECHNICAL PAINT SERVICES

UP88 ONE PACK ETCHING PRIMER

Features:

A liquid plastic copolymer containing a complex formulation of corrosion inhibitors which prevent rust creep. Suitable for application to most ferrous and non-ferrous metals except lead.

Availability:

White, Black, Grey and Red Oxide in 5 and 1 Litre containers.

Volume Solids:

18% ± 3% (BS 3900 Part A10).

Preparation:

The substrate must be thoroughly clean, dry and free from corrosion, dust and grease.

Application:

Brush, roller, conventional spray or dipping. Thin up to 20% by volume with ATR88 One Pack Etch Primer Thinners to achieve a spraying viscosity of 25 - 30 seconds BSB4 cup @ 20°C.

Coverage:

Approximately 45 - 50 sq metres per 5 Litres @ 15 microns dry film thickness.

Drying:

Touch dry: 15 minutes @ 20°C.

Hard dry & recoatable: 45 minutes @ 20°C.

May be stoved for 30 minutes @ 120°C.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.
See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.

FOR PROFESSIONAL USE ONLY. READ DATA BEFORE USE.

27 SOUTHCOTE ROAD BOURNEMOUTH BH1 3SH Tel 0845 230 1244 Fax 0845 230 1255
Email enquiries@technicalpaintservices.co.uk www.technicalpaintservices.com

Technical Paint Services is the trading name of Neatcross Ltd. Registered Office as above. Company No: 1570359.