



TECHNICAL PAINT SERVICES

UP89/25 TWO PACK ETCHING PRIMER

Features:

A two pack zinc chromate primer, comprising an anti-corrosive base and an acid hardener. Essential for use on aluminium and recommended for use on steel, alloys and galvanised surfaces to provide a good key for all paint systems.

Availability:

In 5 and 1 Litre containers.

Volume Solids:

10% ± 3% (BS 3900 Part A10).

Preparation:

The substrate must be thoroughly clean, dry and free from corrosion, dust and grease. Mix UP89 in equal parts by volume with UC89 Two Pack Exterior Etch Primer Catalyst, and allow to stand for 10 minutes before use.

Application:

By conventional spray. Small areas may be brushed. Thinning is not normally required, but if necessary a further 5% of UC89 Catalyst may be added to the mixed material. Use within 4 hours of mixing. The primed surface must be over-coated within 48 hours. Clean equipment and tools with X13 Gunwash.

Coverage:

Approximately 45 - 50 sq metres per 5 Litres mixed @ 10 microns dry film thickness, which is the maximum dry film thickness recommended.

Drying:

Touch dry: 15 minutes @ 20°C.

Hard dry & recoatable: 6 hours @ 20°C.

May be stoved for 30 minutes @ 120°C, after which over-coating may be carried out.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.
See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.

FOR PROFESSIONAL USE ONLY. READ DATA BEFORE USE.

27 SOUTHCOTE ROAD BOURNEMOUTH BH1 3SH Tel 0845 230 1244 Fax 0845 230 1255

Email enquiries@technicalpaintservices.co.uk www.technicalpaintservices.com

Technical Paint Services is the trading name of Neatcross Ltd. Registered Office as above. Company No: 1570359.