



# TECHNICAL PAINT SERVICES

## UP90 TWO PACK EXTERIOR ETCH PRIMER

### **Features:**

A high quality, two pack etching primer which exhibits excellent durability where water resistance and good weathering properties are required. Suitable for application to ferrous and non-ferrous metals, but not lead, UP90 may be over-coated with all paint systems.

### **Availability:**

Grey/Green in 5 and 1 Litre containers.

### **Volume Solids:**

20% ± 3% (BS 3900 Part A10).

### **Preparation:**

The substrate must be thoroughly clean, dry and free from corrosion, mill scale, dust and grease. Mix UP90 in equal parts by volume with UC90 Two Pack Exterior Etch Primer Catalyst, and allow to stand for 10 minutes before use.

### **Application:**

By conventional spray. Small areas may be brushed. Thinning is not normally required, but if necessary a further 10% of UC90 Catalyst may be added to the mixed material. Pot life when mixed is 8 - 10 hours.

### **Coverage:**

Approximately 45 - 50 sq metres per 5 Litres mixed @ 25 microns dry film thickness.

### **Drying:**

Touch dry: 30 minutes @ 20°C.

Recoatable: 1 hour @ 20°C.

May be stoved for 30 minutes @ 120°C, when finishing coats may be applied.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.  
See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.

**FOR PROFESSIONAL USE ONLY. READ DATA BEFORE USE.**