



TECHNICAL PAINT SERVICES

WB176 TWO PACK EPOXY FINISH

Features:

A specially formulated combination of high build modified resin and an epoxy hardener, affording a tough, durable satin finish. Features include: water based, non-flammable, low odour and easy clean-up. Designed as an ideal decorative and protective coating for concrete, cement, rendering, stone, hard and soft wood, ferrous and non-ferrous metals, ceramic and vinyl surfaces.

Availability:

BS4800 colours in 5 Litre composite packs.

Volume Solids:

70% ± 3% (BS3900 Part A10).

Preparation:

Surfaces must be clean, dry and free from wax, grease and oil. Remove all dust and loose particles. New concrete should be allowed to cure thoroughly before painting. On existing painted surfaces, remove all loose and flaking paint and thoroughly rub down with abrasive paper. When used in food preparation areas, it is recommended that surfaces are also treated with ATR131 Anti-Mould Wash before coating.

Application:

Thoroughly mix Pack A with Pack B in the quantities supplied (19 parts Base to 1 part Hardener). Mix up quantities as required for use so as to obtain as long a pot life as possible (maximum pot life 12 hours). After mixing, stir thoroughly before use and allow to stand for 10 minutes. Apply by brush, or for larger areas, a lamb's wool roller. On new or porous surfaces, seal the surface by thinning the first coat with up to 10% of water, following with one or two coats as necessary. **DO NOT APPLY AT TEMPERATURES BELOW 8°C.** Note: The coated surface should not be cleaned with strong alkali detergents or solvents.

Coverage:

Approximately 8 sq metres per Litre depending on the texture and porosity of the substrate.

Drying:

Normally recoatable after 4 hours. When used as a floor sealer, the final coat should be allowed to dry for at least 16 - 24 hours before the floor is returned to use. Ensure adequate ventilation during application and drying.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.
See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.