



TECHNICAL PAINT SERVICES

CONTRACT GRADE ACRYLIC SWIMMING POOL PAINT WBG148

Features:

A contract grade Acrylic Swimming Pool Paint suitable for one to two years use as an affordable refurbishment coating. Suitable for application to all types of porous substrates and other pool coatings, but not suitable for use over two pack epoxy's. Exhibiting excellent water resistance, it is also suitable as a coating for inside concrete ponds. If you wish to paint a newly rendered or concreted surface that is less than 8 - 10 weeks old, it is recommended that you use our Contract Grade Chlorinated Rubber Pool Paint AG148, as this can be applied after just 4 weeks.

Availability:

In Light Blue, Mid Blue & White, 5 Litres minimum. Other colours can be made on an individual basis in minimum quantities of 50 Litres.

Volume Solids:

45% ± 3% (BS 3900 Part A10).

Preparation:

The surface should be thoroughly clean, dry and free from dust and grease. Please see our Swimming Pool Guide for surface preparation guidance to application. This can be downloaded from our web site. Please remember the key to a successful finish is the preparation given to the surface to be coated. Where a pool liner is being removed and you wish to paint the inner surface, we strongly recommend you call our Technical Team before you commence. Where a badly degraded, old or unstable surface exists, it must be stripped prior to application.

Application:

Brush, roller, conventional or airless spray. Supplied ready for use for brushing or rolling. On all new and stripped surfaces a thinned first coat should be applied using clean tap water thinning up to 15% by volume. It is then recommended that a further two full coats be applied to the surface, allowing 4-6 hours drying between coats. After the final coat is applied, the surface should be left for 5 days to fully dry.

Coverage:

Approximately 40 sq metres per 5 Litres, depending on porosity of substrate.

Drying:

Touch dry: 30 minutes @ 20°C.
Hard dry & recoatable: 4-6 hours @ 20°C.
Fully dry: Minimum 5 days.

The foregoing information is given in good faith, based upon tests and experience. It should be noted that recommendations are made without guarantee, as the use of this product is beyond our control.
See Standard Conditions of Sale.

Before using any product, please read the appropriate Material Safety Data Sheet and carry out a full risk assessment for the intended use and method of application.